

Rutting Study of 854 Type B Mixes

Mix ID	470	379	153	471
Design Type	Heavy	Medium	Heavy	Heavy
Binder Content (%)	6.9	7.9	6.9	6.9
Nat Sand (%)	30	40	45	15
deformation mm @ 130F	3.2	7.2	1.9	1.0
deformation mm @ 140F	4.1	12.2	3.0	2.1
deformation mm @ 150F	4.6	8.8	4.0	2.8

All Designs use 76-22 w/ sbs

Use 5 mm for limit on typical test for heavy dense grade mix