

ITEM T-32 COMPOSITION OF SURFACE COURSES

Schedule	Approximate compacted depth including Seal Coats	ROAD MIX						SEAL COATS									
		Aggregate			Bituminous Material			Intermediate Seal				Final Seal					
		Amt. Lbs. per Sq. Yd.	Quality	Size	Kind	Approximate No. gal. per Sq. Yd.		Bituminous Material		Cover Material		Bituminous Material		Cover Material			
						Stone or Gravel	Slag	Gal. per Sq. Yd.	Kind	Quality	Lbs. per Sq. Yd.	Size	Gal. per Sq. Yd.	Kind	Quality	Lbs. per Sq. Yd.	Size
A	2½"	200	M-3.1	No. 34	M-5.6 A.C.B.	1.08	143	0.30	M-5.2 H.O.	M-3.1	18	No. 46	0.25	M-5.6 A.C.B.	M-3.1	16	No. 6
		170	M-3.6		‡M-5.7 A.E.					‡M-5.13 M.T.				M-3.6	15		
B	2"	170	M-3.1	No. 34	M-5.6 A.C.B.	.97	126	0.30	M-5.2 H.O.	M-3.1	18	No. 46	0.25	M-5.6 A.C.B.	M-3.1	16	No. 6
		140	M-3.6		‡M-5.7 A.E.					‡M-5.13 M.T.				M-3.6	15		
C	1½"	135	M-3.1	No. 4	M-5.6 A.C.B.	.86	1.19	0.25	M-5.2 H.O.	M-3.1	14	No. 6	0.25	M-5.6 A.C.B.	M-3.1	16	No. 6
		110	M-3.6		‡M-5.7 A.E.					‡M-5.13 M.T.				M-3.6	11		
D	1"	90	M-3.1	No. 46	M-5.6 A.C.B.	.75	1.10	No intermediate seal				0.30	M-5.6 A.C.B.	M-3.1	22	No. 6	
		76	M-3.6		‡M-5.7 A.E.			‡M-5.13 M.T.	M-3.6	16	M-5.7 A.E.		M-3.6	18			M-5.13 M.T.

‡ Bituminous material A.E. (Sec. M-5.7) shall not be used with slag in the road mix, but is permitted in the final seal coat.

The following table is to be placed in a prominent position on the Typical Section Sheet and all quantities and descriptions filled in for the schedule set up for the project:

ITEM T-32 COMPOSITION OF SURFACE COURSE

Schedule	Approximate compacted depth including Seal Coats	ROAD MIX						SEAL COATS									
		Aggregate			Bituminous Material			Intermediate Seal				Final Seal					
		Amt. Lbs. per Sq. Yd.	Quality	Size	Kind	No. gal. per Sq. Yd.		Bituminous Material		Cover Material		Bituminous Material		Cover Material			
						Stone or Gravel	Slag	Gal. per Sq. Yd.	Kind	Quality	Lbs. per Sq. Yd.	Size	Gal. per Sq. Yd.	Kind	Quality	Lbs. per Sq. Yd.	Size
—	—	—	M-3.1	—	M-5.6 A.C.B.	—	—	—	—	—	—	—	—	M-5.6 A.C.B.	M-3.1	—	—
—	—	—	M-3.6	—	‡M-5.7 A.E.	—	—	—	—	—	—	—	—	M-5.7 A.E.	M-3.6	—	No. 6
—	—	—	*M-3.92	—	‡M-5.13 M.T.	—	—	—	—	—	—	—	—	M-5.13 M.T.	M-3.92	—	—

‡ Bituminous material A.E. (Sec. M-5.7) shall not be used with slag in the road mix, but is permitted in the final seal coat.

* Aggregate sec M-3.92 to be used in schedules "C" and "D", Road Mix only.

Approximate estimated quantities are computed upon the basis of using Stone Sec. M-3.1 and bituminous material Sec. M-5.6.

APPROVED E.H. CHIEF ENGR. CONST.
SEPTEMBER 5, 1933